




Granulats : Gravier Roulé Lavé 11.2/22.4
Péetrographie : Alluvionnaire
Elaboration : Roulé Lavé
Usage : Bétons hydrauliques

Classe granulaire		Partie contractuelle						Catégorie	
11.2	22.4	Norme NF P 18-545 Article 10						Code A	
		d/2	d	D	1.4D	2D	FI	W	
		0.063	5.6	11.2	22.4	31.5	45		
Etendue e			15	15					
V.S.S.+U		6	20	100			24.00		
V.S.S.	1.5	5	15	99			20.00		
V.S.I.			0	84	98	100			
V.S.I.-U			0	79	97				

Partie informative								
Résultats de production								
du 15/04/24 au 09/12/24								
	0.063	5.6	11.2	22.4	31.5	45	FI	W
Maximum	0.5	1	2	91	100	100	10.10	1.6
Moyenne Xf	0.4	1	2	88	100	100	7.42	1.2
Minimum	0.2	0	1	86	100	100	5.90	0.6
Ecart-type	0.07	0.1	0.5	1.3	0.0	0.0	1.538	0.20
Nombre de résultats	22	22	22	22	22	22	5	22



DRUET Marion Responsable QSE